



500

DeccoFloor

FLEXIBLE CONCRETE

ULTRA THIN - EXTREME RESISTANT PAVEMENT

Ultra thin low-cost coating specially designed to reach the highest standards of mechanical resistant.

Fast and easy to apply, only one coat, no sand needed, DECCOFLOOR 500 is the ultimate solution for high traffic projects.

TARGETS

- ✓ Driveways
- ✓ Parking Lots
- ✓ Commercial Stores
- ✓ Warehouses
- ✓ Backyards
- ✓ Schools
- ✓ Malls



ONE COAT ONLY

High Resistance To Chemical Abrasion
Uv Stable



TECHNICAL DATA	PRODUCT COMPOSITION
<p>Tipo: Micro concrete.</p> <p>Aspecto: White Powder.</p> <p>Apparent density: Powder: 1.300 kg/m³</p> <p>Solids content: 100%</p> <p>Open time: 60 minutes. re-mix every 15 minutes.</p> <p>Addition of water: ± 18-20%</p> <p>Maximum aggregate size: 0,6 mm</p> <p>Mechanical Strength(EN 1015-11): Compression 28 days: 45N/mm². Flexion 28 days: 8N/mm².</p> <p>Adhesion to concrete: 28 days: 28 días: ≥2N/mm².</p> <p>Thickness per coat.: 0,6 mm. Fire reaction (EN 13501-1): A1.</p>	<ul style="list-style-type: none"> - Microconcrete - Mineral fillers <p style="text-align: right;">86.5%</p> <ul style="list-style-type: none"> - organic resins - Correctors <p style="text-align: right;">13.5%</p> <p>According to UNE EN 13892</p> <p>Class: A22 C45 F8 B2</p>

SURFACE PREPARATION: The surface should be clean and dry. For a proper application, moisten the surface with Deccofloor Primer is recommended.

PRE-APPLICATION: In a clean bucket pour the material and add water up to the 25%-30% ratio, mix the product with a low revolution driller (300-500 rpm) for at least 3 minutes, let it stand for 10 minutes and then stir it again for 2 more minutes until getting a uniform mixture.

APPLICATION: Apply at least 1 coat of Deccofloor 500 stirring it with a stain steel trowel (also a squeegee may be used). Only sand if you want to get a more flatted finished. Apply Deccofloor Eco Seal uniformly is recommended for better results.

COVERAGE: Up to 350 sq ft per coat (average). Coverage rates may vary depending on a surface porosity, texture, the application method and other local conditions.

PACKAGING: 48 lbs bucket.